


**Model:** CONCEPT WHITE PULIDO 60X60(A)  
**Codes:** 100140185 - C225953991  
**Water absorption:** Bla - Porcelain tiles ( $E \leq 0.1\%$ )  
**Thickness:** 11/32 " approx.  
**Family:** CONCEPT  
**Tone variations:** V3  
**Finish:** POLISHED



### DIMENSIONAL FEATURES

Thickness	11/32 " approx.	
Width	23 19/32 " approx.	
Length	23 19/32 " approx.	
Length and width deviation	Below 0.15%	$\leq 0.5\%$ *
Side straightness deviation	Below 0.15%	$\leq 0.5\%$ *
Squareness deviation	Below 0.15%	$\leq 0.6\%$ *
Surface flatness deviation	Below 0.15%	$\leq 0.5\%$ *
Thickness tolerance	5 DMM	

### MECHANICAL FEATURES

Breaking strength	> 539,76 LBF	>292 LBF*
Abrasion resistance	<130	

### HYGIENIC FEATURES

Stain resistance	Class 5. Easy cleaning with water	CLASE 3 Min. *
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	CLASE B Min. *

### ANTI-SLIP VALUE

Friction (dry)	0.65	
Friction (wet)	0.36	
Slip resistance (pendulum-dry)	>65	
4s	DRY>36-LOW WET<25-HIGH	

### SCOPE OF USE

Technical code-1	Use on light traffic floors	
------------------	-----------------------------	--

### PACKING

Boxes	15,5 SQF/CS	
Pallets	496 SQF/PAL	
Units	3,88 SQF/ST	

Certified company



A DCOF value of > 0.42 is the new standard for tiles specified for commercial level interior applications expected to be walked upon when wet, in standard A137.1-2012. It replaces the SCOF value of > 0.60 referenced in ADA Guidelines (measurement made as per the ASTM C1028 test method) However, there are many factors that affect the possibility of a slip occurring and then tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine if tiles are appropriate for specific project conditions, considering by way of example, but not limited to; type of use, traffic, expected contaminants, expected maintenance, expected wear and manufacturer guidelines and recommendations. Tiles with a DCOF inferior to 0.42 shall only be installed when the surface will kept dry when walked upon and proper safety procedures are followed when cleaning the tiles.

A DCOF value of > 0.42 is the new standard for tiles specified for commercial level interior applications expected to be walked upon when wet, in standard A137.1-2012. It replaces the SCOF value of > 0.60 referenced in ADA Guidelines (measurement made as per the ASTM C1028 test method) However, there are many factors that affect the possibility of a slip occurring and then tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine if tiles are appropriate for specific project conditions, considering by way of example, but not limited to; type of use, traffic, expected contaminants, expected maintenance, expected wear and manufacturer guidelines and recommendations. Tiles with a DCOF inferior to 0.42 shall only be installed when the surface will kept dry when walked upon and proper safety procedures are followed when cleaning the tiles.