

**Model:** ARS BEIGE NAT. (S/R)MLL 162X324(12)(A)


**Codes:** 100213103 - C279014431

**Absorption:** Bla - Porcelain tiles ( $E \leq 0.1\%$ )

**Thickness:** 12 mm

**Family:** ARS

**Tone variations:** V4



### DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

Length	3240 MM	
Thickness	12 MM	
Width	1620 MM	
Length and width deviation	Below 0.15%	$\leq 0.5\%*$
Side straightness deviation	Below 0.15%	$\leq 0.5\%*$
Squareness deviation	Below 0.15%	$\leq 0.6\%*$
Surface flatness deviation	Below 0.15%	$\leq 0.5\%*$

\*ISO-13006:2012 UNE-EN 14411:2012

### MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-11

Breaking strength	>3000 N	
Modulus of rupture	>45 N/MM <sup>2</sup>	
Abrasion resistance	<140	
Crazing resistance	Resists 3 cycles	

\*ISO-13006:2012 UNE-EN 14411:2012

### HYGIENIC FEATURES

UNE-EN ISO 10545-13-14:1995

Chemical resistance	CLASE A	
Stain resistance	5	

\*ISO-13006:2012 UNE-EN 14411:2012

### ANTI-SLIP VALUE

UNE-ENV 12633:2003, DIN-51130 y ASTM C1028

Slip resistance (pendulum-wet)	CL1	
Stain resistance	5	
4s	DRY>36-LOW WET>24-MODERATE	

\*ISO-13006:2012 UNE-EN 14411:2012

### SCOPE OF USE

Technical code-1	Use on walls	
Technical code-2	No additional requirements	

### PACKING

Boxes	1 ST/CS	
Pallets	16 ST/PAL	

Certified company



A DCOF value of > 0.42 is the new standard for tiles specified for commercial level interior applications expected to be walked upon when wet, in standard A137.1-2012. It replaces the SCOF value of > 0.60 referenced in ADA Guidelines (measurement made as per the ASTM C1028 test method) However, there are many factors that affect the possibility of a slip occurring and then tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine if tiles are appropriate for specific project conditions, considering by way of example, but not limited to; type of use, traffic, expected contaminants, expected maintenance, expected wear and manufacturer guidelines and recommendations. Tiles with a DCOF inferior to 0.42 shall only be installed when the surface will kept dry when walked upon and proper safety procedures are followed when cleaning the tiles.

A DCOF value of > 0.42 is the new standard for tiles specified for commercial level interior applications expected to be walked upon when wet, in standard A137.1-2012. It replaces the SCOF value of > 0.60 referenced in ADA Guidelines (measurement made as per the ASTM C1028 test method) However, there are many factors that affect the possibility of a slip occurring and then tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine if tiles are appropriate for specific project conditions, considering by way of example, but not limited to; type of use, traffic, expected contaminants, expected maintenance, expected wear and manufacturer guidelines and recommendations. Tiles with a DCOF inferior to 0.42 shall only be installed when the surface will kept dry when walked upon and proper safety procedures are followed when cleaning the tiles.